



# SPEC DATA SHEET

# DIVOT PATCH

## PRODUCT DESCRIPTION

Versatile Building Products DIVOT PATCH is a specially formulated blend of fast-setting, shrinkage compensated cements and polymer, designed to fill and smooth virtually all masonry surfaces. Use DIVOT PATCH to fill in surface defects such as spalls, gouges, cracks, dents, chips, scrapes, and honeycombs to true featheredge finish.

## COMPOSITION

Special proprietary blend of wetting agents, fillers, high strength cement, surfactants and latex polymers.

## ADVANTAGES

- Rapid hardening
- Just add water and mix
- Self curing
- Finish to a feathered edge

## LIMITATIONS

- Do not force dry
- Coverage rates may vary.
- Always wear protective clothing and equipment as required by OSHA and as necessary.
- Read Material Safety Data Sheets before commencing work.
- Material is not intended for use in submerged water or constant moisture conditions.

## AREAS OF USE

- Garage Floors
- Industrial Floors
- Any Concrete Surface
- Previously Coated Floors

## COLORS

Dark Gray

## PACKAGING and COVERAGE

### 5Lb Package

#### Thickness

1/8 -inch	5 sq. ft
1/4 -inch	2.5 sq. ft

### 50 Lb Pail

#### Thickness

1/8 -inch	50 sq. ft
1/4 -inch	25 sq. ft

## FINISHES

Smooth

## AVAILABILITY AND COST

VBP Products are supplied direct and all prices, install guides, etc are viewable online at [www.garagecoatings.com](http://www.garagecoatings.com).

## INSTALLATION

Refer to manufacturers detailed System Installation Guide.

## COVERAGE

Refer to manufacturers detailed System Installation Guide.

## MAINTENANCE

Maintain the protective topcoat or subsequent layer to prevent damage of the DIVOT PATCH. If the DIVOT PATCH is damaged, it can be repaired by sanding the surface, cleaning and then recoating the area with same materials.

## TECHNICAL SERVICES

Technical services can be obtained by contacting: VBP direct at 714-829-2600.

## TECHNICAL DATA

### Properties

<b>Application Thickness</b>	1/16-3/16"
------------------------------	------------

<b>VOC</b> (Volatile Organic Compounds)	0g/L
---	------

<b>Working time,</b>	~20min
----------------------	--------

<b>Open to foot traffic</b>	<2 Hours
-----------------------------	----------

<b>Elongation</b> (ASTM C-307)	1.02%
-----------------------------------	-------

<b>Tensile Strength</b> (ASTM C-307)	625 p.s.i.
---	------------

<b>Flexural Strength</b> (ASTM C-580)	1000 p.s.i.
--	-------------

245 CARL KARCHER WAY  
ANAHEIM, CA 92801  
TEL: (714) 829-2600

[www.deckcoatings.com](http://www.deckcoatings.com) [www.garagecoatings.com](http://www.garagecoatings.com)

**PROPERTIES (continued)**

**Compressive Strength** 4200 p.s.i.  
(ASTM C-109)

**Adhesion** 350p.s.i.  
(ACI 503R) (100% Concrete failure)

**Flammability** Self extinguishing  
over concrete

**Warranty**

Versatile Building Products Inc guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. Versatile Building Products Inc (herein referred to as "seller") makes no warranty, expressed or implied, regarding the use of its products. Since use of this product is beyond the seller's control, the buyer assumes all risk of use. Seller's obligation shall be to replace material if found defective. Seller shall not be liable for any damage, injury, loss, direct or consequential, resulting from the use of its products. End user must determine if substrate is suitable for coating application before installing.